

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
21 April 2005 (21.04.2005)

PCT

(10) International Publication Number
WO 2005/035438 A1

(51) International Patent Classification⁷: **B81C 1/00, G03F 7/00, B82B 3/00, B05D 1/28**

(21) International Application Number:
PCT/IB2004/052009

(22) International Filing Date: 7 October 2004 (07.10.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
0323902.7 11 October 2003 (11.10.2003) GB

(71) Applicant (for all designated States except US): **KONINKLIJKE PHILIPS ELECTRONICS N.V.** [NL/NL];
Groenewoudseweg 1, NL-5621 BA Eindhoven (NL).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **BURDINSKI, Dirk** [DE/DE]; c/o Philips Intellectual Property & Standards, Cross Oak Lane, Redhill, Surrey RH1 5HA (GB).

SHARPE, Ruben, B., A. [NL/NL]; c/o Philips Intellectual Property & Standards, Cross Oak Lane, Redhill, Surrey RH1 5HA (GB).


(74) Agent: **WHITE, Andrew, G.**; c/o Philips Intellectual Property & Standards, Cross Oak Lane, Redhill, Surrey RH1 5HA (GB).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.


(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,

[Continued on next page]

(54) Title: METHOD FOR PATTERNING A SUBSTRATE SURFACE



e



f

(57) Abstract: An elastomeric stamp (10) is provided, which has a bulk surface (12) from which protruding features (14, 14') extend. A barrier layer (20) covers the bulk surface (12) and the protruding features (14, 14'). After applying an ink solution to the elastomeric stamp (10) and drying the elastomeric stamp (10), the elastomeric stamp (10) is brought into contact with a surface (42) of a first substrate (40). The surface (42) of the first substrate (40) has a high affinity with the ink molecules (32), which is utilized to effectively remove the ink molecules (32) from the contact surfaces (16, 16') of the protruding features (14, 14'). Subsequently, the elastomeric stamp (10) is brought into contact with the surface (52) of a second substrate (50). Ink molecules 32 are transferred from the edges (18, 18') of the protruding features (14, 14') to the surface (52) of a second substrate (50), thus forming an ink pattern in the form of a selfassembled monolayer on this surface (52). The patterning method of the present invention allows for the formation of high-definition ink patterns on a substrate (50) using a wide variety of inks.



ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,
FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI,
SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ,
GW, ML, MR, NE, SN, TD, TG).

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

Published:

— *with international search report*